## Determination of formaldehyde release according to the standard SFS-EN ISO 12460-3

Requested by: Nallekuja 5, FI-01900 Nurmijärvi, Finland





Customer/ Requested by	y Nordstock Oy Jari Vinha Nallekuja 5 FI-01900 Nurmijärvi FINLAND
Order	Jari Vinha, 2.10.2017
Our reference number	OM 190890
Contact person	VTT Expert Services Ltd Senior Laboratory Technician Jouni Penttilä P.O. Box 1001 FIN-02044 VTT Tel. +358 40 720 7431 E-mail: jouni.penttila@vtt.fi
Assignment	Determination of formaldehyde release according to the standard

EN	717	-2

SampleTwo test pieces (400 mm x 50 mm) for the formaldehyde analysis of MDF sheet<br/>marked as Gizir Acrylic panel was sent to VTT Expert Services Ltd by the client<br/>on the 3<sup>rd</sup> of October 2017. The pieces were packed in inside a plastic and a<br/>pasteboard package. It was received at VTT Expert Services Ltd on the 3<sup>rd</sup> of<br/>October 2017. The sample was not conditioned before testing.

**Performance of the test** Formaldehyde release of the sample was determined by the gas analysis method according to the standard SFS-EN ISO 12460-3

The tests were performed between on the  $5^{th}$  and on the  $6^{th}$  of October 2017.

**Test result** The test results were:

Sample	Moisture content %	Formaldehyde release mg/(m²h)
Nordstock / Gizir Acrylic panel A010	-	3.0

The accuracy of the measuring method is  $\pm\,20\%$  . The test results are valid only for the tested sample.

The use of the name of VTT Expert Services Ltd or the name Technical Research Centre of Finland (VTT) in any other form in advertising or publication in part of this report is only permissible with written authorisation from VTT Expert Services Ltd.

The test results relate only to the sample tested.



**Observations** The test result is in accordance with the E1 requirement of  $\leq 3.5 \text{ mg/m}^2\text{h}$  (EN13986/2015).

Espoo, October 26<sup>th</sup> 2017

Helena Järnström Product Manager Jouni Penttilä Senior Laboratory Technician

Distribution

Customer Archive Original Original

The test results relate only to the sample tested.

The use of the name of VTT Expert Services Ltd or the name Technical Research Centre of Finland (VTT) in any other form in advertising or publication in part of this report is only permissible with written authorisation from VTT Expert Services Ltd.